SEARCH REQUEST FORM **Scientific and Technical Information Center - EIC2800**

Rev. 8/27/01 This is an experimental format -- Please give suggestions or comments to Jeff Harrison, CP4-9C18, 306-5429.

Date 5/2/03 Serial # 09/602,395 Priority Application Date 6/22/00

Your Name Thanhha Pham Examiner # 77623

AU 2813 Phone 308-6172 Room CP4-4D19

In what format would you like your results? Paper is the default. PAPER DISK EMAIL

If submitting more than one search, please prioritize in order of need.

The EIC searcher normally will contact you before beginning a prior art search. If you would like to sit with a searcher for an interactive search, please notify one of the searchers.

Where have you searched so far on this case?

Circle: USPT DWPI EPO Abs JPO Abs IBM TDB

Other: _____

What relevant art have you found so far? Please attach pertinent citations or Information Disclosure Statements. 6,436,771

What types of references would you like? Please checkmark:

Primary Refs ___ Nonpatent Literature ___ Other _____

Secondary Refs ___ Foreign Patents ___

Teaching Refs ___

What is the topic, such as the **novelty**, motivation, utility, or other specific facets defining the desired **focus** of this search? Please include the concepts, synonyms, keywords, acronyms, registry numbers, definitions, structures, strategies, and anything else that helps to describe the topic. Please attach a copy of the abstract and pertinent claims.

Nitridation ; then oxidation surface with oxide layer & silicon surface to form different thickness gate oxides

Staff Use Only	Type of Search	Vendors
Searcher: _____	Structure (#)_____	STN_____
Searcher Phone: _____	Bibliographic_____	Dialog_____
Searcher Location: STIC-EIC2800, CP4-9C18	Litigation_____	Questel/Orbit_____
Date Searcher Picked Up: _____	Fulltext_____	Lexis-Nexis_____
Date Completed: _____	Patent Family_____	WWW/Internet_____
Searcher Prep/Rev Time: _____	Other_____	Other _____
Online Time: _____		

US006436771B1

(12) **United States Patent**
Jang et al.

(10) **Patent No.: US 6,436,771 B1**
(45) **Date of Patent: Aug. 20, 2002**

(54) METHOD OF FORMING A SEMICONDUCTOR DEVICE WITH MULTIPLE THICKNESS GATE DIELECTRIC LAYERS

(75) Inventors: Syun-Ming Jang; Chen-Hua Yu; Mong-Song Liang, all of Hsin-Chu (TW)

(73) Assignee: Taiwan Semiconductor Manufacturing Company, Hsin-Chu (TW)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: 09/902,895

(22) Filed: Jul. 12, 2001

(51) Int. Cl.[7] H01L 21/8234

(52) U.S. Cl. 438/275; 438/216; 438/279; 438/286; 438/287; 438/528; 438/591; 438/981

(58) Field of Search 438/197, 216, 438/230, 275, 279, 286, 287, 528, 585, 591, 981

(56) References Cited

U.S. PATENT DOCUMENTS

5,254,489	A	10/1993	Nakato	437/69
5,719,085	A	2/1998	Arai	438/981
5,763,922	A	6/1998	Chau	257/371
5,960,962	A	11/1999	Holloway et al.	438/275
6,048,769	A	4/2000	Chau	438/275
6,093,661	A *	7/2000	Trivedi et al.	438/769
6,171,941	B1 *	1/2001	Yu	438/275

* cited by examiner

Primary Examiner—Chandra Chaudhari
Assistant Examiner—Jack Chen
(74) Attorney, Agent, or Firm—George O. Saile; Stephen B. Ackerman

(57) ABSTRACT

Process sequences used to simultaneously form a first dielectric gate layer for a first group of MOSFET elements, and a second dielectric gate layer for a second group of MOSFET elements, with the thickness of the first dielectric gate layer different than the thickness of the second gate dielectric layer, has been developed. A first iteration of this invention entails a remote plasma nitridization procedure used to form a thin silicon nitride layer on a bare, first portion of a semiconductor substrate, while simultaneously forming a thin silicon oxynitride layer on the surface of a first silicon dioxide layer, located on second portion of the semiconductor substrate. A thermal oxidation procedure than results in the formation of a thin second silicon dioxide layer, on the first portion of the semiconductor substrate, underlying the thin silicon nitride layer, while the first silicon dioxide layer, underlying the silicon oxynitride component of the composite dielectric layer, only increases slightly in thickness. A second iteration of this invention features the formation of a silicon nitride—first silicon dioxide, composite gate layer, on a first portion of a semiconductor substrate, with the composite gate layer used to retard oxidation during a thermal oxidation procedure used growth to form a second silicon dioxide layer, on a second portion of the semiconductor substrate

8 Claims, 4 Drawing Sheets